

# PRODUCT DATA SHEET

## Sikasil® Universal

Silicone sealant for universal use

### PRODUCT DESCRIPTION

Sikasil® Universal is a 1-part, acetoxy curing silicone joint sealant which provides an elastic waterproof seal.

### USES

- Waterproofing various types of construction joints
- For interior and exterior use

### CHARACTERISTICS / ADVANTAGES

- Low-modulus
- High elasticity
- Movement capability  $\pm 20\%$
- Primerless application for many substrates
- Good adhesion to a range of substrates
- Good resistance to UV exposure
- Solvent free (acc. to TRGS 610)

### APPROVALS / STANDARDS

- CE Marking and Declaration of Performance to EN 15651-1 - Sealants for non-structural use in joints in buildings - Facade elements
- CE Marking and Declaration of Performance to EN 15651-2 - Sealants for non-structural use in joints in buildings - Sealants for glazing

### PRODUCT INFORMATION

Chemical Base	Acetoxy silicone
Packaging	280 ml cartridges: 12 cartridges per box Refer to current price list for packaging variations
Colour	Colour range to be defined by local sales organisation
Shelf Life	18 months from date of production
Storage Conditions	The product must be stored in original, unopened and undamaged packaging in dry conditions at temperatures between +5 °C and +25 °C. Always refer to packaging.
Density	~1,00 kg/l (ISO 1183-1)
Product Declaration	EN 15651-1: F EXT-INT CC EN 15651-2: G CC

### TECHNICAL INFORMATION

Shore A Hardness	~20 (after 28 days) (ISO 868)
------------------	-------------------------------

<b>Tensile Strength</b>	~1,8 N/mm <sup>2</sup>	(ISO 8339)
<b>Secant Tensile Modulus</b>	~0,35 N/mm <sup>2</sup> at 100 % elongation (+23 °C)	(ISO 8339)
<b>Elongation at Break</b>	~550 %	(ISO 37)
<b>Elastic Recovery</b>	>90 %	(ISO 7389)
<b>Tear Propagation Resistance</b>	~2,6 N/mm	(ISO 34)
<b>Movement Capability</b>	±20 %	(ISO 9047)
<b>Service Temperature</b>	-40 °C min / +100 °C max	
<b>Joint Design</b>	The joint dimensions must be designed to suit the movement capability of the sealant. For joint widths more than 10 mm and less than 20 mm, a joint depth of 10 mm is recommended. For larger joints contact Sika Technical Services for additional information.	

## APPLICATION INFORMATION

Consumption	Joint width [mm]	Joint depth [mm]	Joint length [m] per 280 ml
	10	10	2,8
15	10	1,8	
20	10	1,4	

Consumption depends on the roughness and absorbency of the substrate. These figures are theoretical and do not allow for any additional material due to surface porosity, surface profile, variations in level or wastage etc.

<b>Sag Flow</b>	< 1 mm (20 mm profile, +23 °C)	(ISO 7390)
<b>Ambient Air Temperature</b>	+5 °C min. / +40 °C max.	
<b>Substrate Temperature</b>	+5 °C min. / +40 °C max. Minimum +3 °C above dew point temperature	
<b>Curing Rate</b>	~3,0 mm/24 hours (+23 °C / 50 % r.h.)	(CQP* 049-2) * Sika Corporate Quality Procedure
<b>Skin Time</b>	~25 min (+23 °C / 50 % r.h.)	(CQP 019-1)

## VALUE BASE

All technical data stated in this Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

## FURTHER DOCUMENTS

- Sika Pre-treatment Sealing and Bonding Chart

## LIMITATIONS

- Sikasil® Universal cannot be overpainted.
- Colour variations may occur due to the exposure in service to chemicals, high temperatures and/or UV-radiation (especially with white colour shade). This effect is aesthetic and does not adversely influence the technical performance or durability of the product.
- Do not use on bituminous substrates, natural rubber, EPDM rubber or on any building materials which might leach oils, plasticisers or solvents that could degrade the sealant.
- Do not use in totally confined spaces as it requires

atmospheric moisture to cure.

- Sikasil® Universal is not recommended for porous substrates, such as concrete, stone, marble and granite. Staining from plasticiser migration may occur when used on these substrates. Preliminary trials must be carried out to check if the substrate experiences staining before full project application.
- Do not use where physical or abrasion exposure is likely to occur, structural glazing and insulated glazing or food contact applications. Contact Sika Technical Services for advice on alternative products.
- Do not use for medical or pharmaceutical uses.
- Acetic acid released during curing can cause the corrosion of mirror silver and sensitive metals such as copper, brass and lead.
- Do not use on alkaline surfaces such as concrete, plaster, render and brick.

## ECOLOGY, HEALTH AND SAFETY

Local safety regulations must be observed and it advisable to wear PPI when working with this product with particular attention paid to cutting and handling. Transportation Class: The product is not classified as

hazardous good for transport. Disposal: The material is recyclable. Disposal must be according to local regulations. Please contact your local Sika sales organisation for more information.

## APPLICATION INSTRUCTIONS

### SUBSTRATE PREPARATION

The substrate must be sound, clean, dry and free of all contaminants such as dirt, oil, grease, cement laitance, old sealants and poorly bonded paint coatings which could affect adhesion of the sealant. The substrate must be of sufficient strength to resist the stresses induced by the sealant during movement.

Removal techniques such as wire brushing, grinding, grit blasting or other suitable mechanical tools can be used.

All dust, loose and friable material must be completely removed from all surfaces before application of any activators, primers or sealant.

Sikasil® Universal adheres without primers and/or activators.

For optimum adhesion, joint durability and critical, high performance applications such as joints on multi-storey buildings, highly stressed joints, extreme weather and / or water exposure. The following priming and/or pre-treatment procedures must be followed:

#### Non-porous substrates

Aluminium, anodised aluminium, stainless steel, PVC, galvanised steel, powder coated metals or glazed tiles. Slightly roughen surface with a fine abrasive pad. Clean and pre-treat using Sika® Aktivator-205 applied with a clean cloth.

Before sealing, allow a waiting time of > 15 minutes (< 6 hours).

Other metals, such as copper, brass and titanium-zinc, cleaned and pre-treat using Sika® Aktivator-205 applied with a clean cloth. After a waiting time of > 15 minutes (< 6 hours). Apply Sika® Primer-3 N by brush. Before sealing, allow a waiting time of > 30 minutes (< 8 hours)

PVC has to be cleaned and pre-treated using Sika® Primer-215 applied with a brush. Before sealing, allow a waiting time of > 30 minutes (< 8 hours).

Glass must be cleaned with Isopropanol before application

#### Porous substrates

Must be primed using Sika® Primer-3 N applied by brush.

Before sealing, allow a waiting time of > 30 minutes (< 8 hours).

Adhesion tests on project specific substrates must be performed and procedures agreed with all parties be-

fore full project application.

Contact Sika Technical Services for additional information.

Note: Primers and activators are adhesion promoters and not an alternative to improve poor preparation / cleaning of the joint surface. Primers also improve the long term adhesion performance of the sealed joint.

### MIXING

1-part ready to use

### APPLICATION METHOD / TOOLS

Strictly follow installation procedures as defined in method statements, application manuals and working instructions which must always be adjusted to the actual site conditions.

#### Masking

It is recommended to use masking tape where neat or exact joint lines are required. Remove the tape within the skin time after finishing.

#### Joint Backing

After the required substrate preparation, insert a suitable backing rod to the required depth.

#### Priming

If required, prime the joint surfaces as recommended in substrate preparation. Avoid excessive application of primer to avoid causing puddles at the base of the joint.

#### Application

Sikasil® Universal is supplied ready to use.

Prepare the end of the foil pack or cartridge, insert into the sealant gun and fit the nozzle. Extrude Sikasil® Universal into the joint ensuring that it comes into full contact with the sides of the joint and avoiding any air entrapment.

#### Finishing

As soon as possible after application, sealant must be firmly tooled against the joint sides to ensure adequate adhesion and a smooth finish.

Use a compatible tooling agent to smooth the joint surface. Water can be used. Do not use tooling products containing solvents.

### CLEANING OF TOOLS

Clean all tools and application equipment immediately after use with Sika® Remover-208. Hardened material can only be removed mechanically. For cleaning skin, use Sika® Cleaning Wipes-100.

## LOCAL RESTRICTIONS

Note that as a result of specific local regulations the declared data and recommended uses for this product

may vary from country to country. Consult the local Product Data Sheet for the exact product data and uses.

## LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

### SIKA IRELAND LIMITED

Ballymun Industrial Estate  
Ballymun  
Dublin 11, Ireland  
Tel: +353 1 862 0709  
Web: [www.sika.ie](http://www.sika.ie)  
Twitter: @Sikalreland



### Product Data Sheet

Sikasil® Universal  
March 2021, Version 02.02  
020514030000000085

SikasilUniversal-en-IE-(03-2021)-2-2.pdf

